



# HOT STUCCO *PRIMER*

## 100% ACRYLIC HOT STUCCO PIGMENTED MASONRY PRIMER/SEALER

Hot Stucco Primer is a 100% acrylic resin that is a rich pigmented primer/sealer designed for application to new masonry surfaces. Hot Stucco Primer is alkali resistant and may be applied to fresh stucco and masonry surfaces. There is no need to wait for the stucco to cure. Hot Stucco Primer may be applied after 24 hours of cure time. This primer is highly resistant to "Hot Stucco."

Fast  
Application

Tough  
& Durable

Alkali  
Resistant

Easy to  
Use

**RECOMMENDED USES:** For use on any new or uncoated masonry or plaster surface.

**SURFACE PREPARATION:** Dirt, grease, grime and any foreign material must be removed before application of new coating. Treat surface for mildew. Be sure surface is clean and dry. Patch all cracks and openings after application of Hot Stucco Primer.

**APPLICATION:** Mix product thoroughly and apply with brush, roller or airless sprayer. When spraying, use a tip designed for flat wall coatings. Apply when surface and air temperatures are above 50 Deg. F.

**RECOMMENDED THINNER:** Hot Stucco Primer does not require thinning use directly as supplied.

**CLEAN UP:** Clean up drips and spills immediately using a damp cloth. Clean tools and equipment with soap and fresh water.

**COVERAGE (THEORETICAL):** Coverage will depend on porosity and contour of the surface being coated. Coverage typically averages 150-250 square feet per gallon.

**Hot Stucco Primer is water based. Do not Freeze.**

|                                          |                                              |
|------------------------------------------|----------------------------------------------|
| Finish:                                  | Low Sheen                                    |
| Vehicle Type:                            | 100% Acrylic                                 |
| Solvent Type:                            | Water                                        |
| % Solids By Weight:                      | 44% +/- 2%                                   |
| % Solids By Volume:                      | 30% +/- 2%                                   |
| Density:                                 | 10.30 lbs. Per gallon                        |
| Viscosity @ 75 deg. F (24 deg. C):       | 100 +/- 2 K.U.                               |
| Coating VOC:                             | < 150 g/l                                    |
| Flash Point, Minimum:                    | Not Flammable                                |
| Flame Spread:                            | Class A rating on non combustible substratum |
| Recommended Dry Film Thickness Per Coat: | 1.0-2.0 MILS DFT.                            |
| Estimated Dry Time:                      | Touch: 30-60 minutes<br>Recoat: 4-6 hours    |

**CAUTION: KEEP OUT OF REACH OF CHILDREN! WARNING!** If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear an NIOSH approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). Technical data contained here in is true and accurate at the date of issue, but is subject to change without notice. An INSECO representative should be contacted with any questions concerning product information or application procedures. Our products conform to INSECO quality standards, but no other warranty is expressed or implied. Liability, if any, is limited to the replacement of product or purchase price.



# INSECO

INSECO, Inc.  
2897 South Street  
Fort Myers, FL 33916

[insecoproducts.com](http://insecoproducts.com)  
(800) 883-5150  
[info@insecoproducts.com](mailto:info@insecoproducts.com)